



DATA SHEET
DS 115
Rev. 7 dd 17/04/2015
INETIG 100

I.N.E. S.p.A.
 Via Facca 10
 35013 Cittadella (PADOVA)
 ITALY
 Tel. : +39 049/9481111 Fax: + 39 049/9400249
 Internet: www.ine.it E mail: ine@ine.it

CLASSIFICATION

AWS SPECIFICATIONS	EN SPECIFICATIONS
AWS A 5.28: ER100S-1	EN ISO 16834-A: W 62 5 I1 Mn3Ni1,5Mo
AWS A 5.28M: ER69S-1	
ASME SFA 5.28: ER100S-1	
ASME SFA 5.28M: ER69S-1	

APPROVALS

ALLOY TYPE

Copper-coated tig rod for welding high strength steels.

APPLICATIONS

Low-alloy copper-coated tig rod with Ni-Mo additions designed for welding high yield strength steels and with tensile strength higher than 700 MPa. Good impact strength at low temperatures. Suitable for the metal working industry, offshore fabrication, chemical and petrochemical industry. It also has applications in fabrications of HSLA (high-strength low-alloy) steels, which may be used for industrial machinery construction, cranes and other highly stressed structural components.

MATERIALS TO BE WELDED

ASTM		EN		Others
A 514	API 5LX X65	10137-2 S460	10208-2 L480	RQT 601
A 517	API 5LX X70	10137-2 S500	10208-2 L550	Navy Q1
HY80	API 5LX X80	10137-2 S550	(BS 4360 Gr 55F)	NAXTRA 70
HY90	API 5A L80	10137-2 S620		WELDOX 700
HY100		10137-2 S690		

WELDING GUIDELINES

Preheat and interpass temperature 150°C. PWHT is not required. To obtain the best mechanical properties results, the use with low heat input is advised (follow the steel producer recommendations).

TECHNICAL INFORMATION

Gas: Argon 100% (EN ISO 14175)
 Welding position: all positions



WELDING PARAMETERS

Current	DC - Straight polarity
----------------	-------------------------------

PACKAGING DATA

Diameter (mm)	1.2	1.6	2.0	2.4	3.2	4.0
Length (mm)	1000	1000	1000	1000	1000	1000
Carton	5/25 Kg	5/25 Kg	5/25 Kg	5/25 Kg	5/25 Kg	5/25 Kg

* tolerances according to EN ISO 544 specification.



DATA SHEET
DS 115
Rev. 7 dd 17/04/2015
INETIG 100

I.N.E. S.p.A.
Via Facca 10
35013 Cittadella (PADOVA)
ITALY
Tel. : +39 049/9481111 Fax: + 39 049/9400249
Internet: www.ine.it E mail: ine@ine.it

TYPICAL CHEMICAL COMPOSITION OF WIRE

C %	Mn %	Si %	S %	P %	Cu %	Ni %	Cr %	Mo %	
0.07	1.50	0.50	0.007	0.007	0.12	1.60	0.05	0.45	

TYPICAL MECHANICAL PROPERTIES

GAS		Yield strength	Tensile strength	Elongation on % 5d	Impact energy (Charpy V)				
		Rs	Rm	A 5d	+ 20°C	0°C	-20°C	-40°C	-50°C
		(MPa)	(MPa)	%	(Joule)	(Joule)	(Joule)	(Joule)	(Joule)
I1	as welded	640	720	22	-	-	-	90	80

PRODUCTS AVAILABLE

Process	Product	Classification AWS	Classification EN
MIG/MAG Solid wire	INEFIL 100	AWS A 5.28: ER100S-1	EN 16834-A: G Mn3Ni1,5Mo
	INEFIL NIMOCR	AWS A 5.28: ER100S-G	EN 16834-A: G Mn3Ni1CrMo
	INEFIL 110	AWS A 5.28: ER110S-1	(EN 16834-A: G Mn3Ni2,5CrMo)
	INEFIL 70	AWS A 5.28: ER100S-G	EN 16834-A: G Mn3NiCrMo
	INEFIL NIMO	AWS A 5.28: ER100S-G	EN 16834-A: G Mn3Ni1Mo
TIG Rods	INETIG 110	AWS A 5.28: ER110S-1	(EN 16834-A: W Mn3Ni2,5CrMo)
SAW Submerged arc	INESUB S3NIMO	AWS A 5.23: EG	EN 26304-A: S3Ni1Mo
	INESUB EF3	AWS A 5.23: EF3	EN 26304-B: SUN2M33
FCAW Cored wire	INETUB M111TG-K3	AWS A 5.28: E110C-K3	EN 18276-A: T 2NiMo
	INETUB M91TG	AWS A 5.28: E90C-G	EN 18276-A: T 55 5 Z M M
	INETUB M121TG-K4	AWS A 5.28: E120C-K4	EN 18276-A: T Mn2NiCrMo
	INETUB B121T5-K4	AWS A 5.29: E121T5-K4	EN 18276-A: T Mn2NiCrMo
SMAW Electrodes	INE 80 B	AWS A 5.5: E10018M	EN 18275-A: E 1NiMo